

# CuZn15

EN\_2024\_03

Comparable standards: UNS C23000 • EN CW502L • JIS C2300  
 Aurubis designations: C230 • SM 1085 • PNA 223

## Description

CuZn15 is a solid solution strengthened copper alloy containing 15% zinc (brass). CuZn15 has very good cold formability and is suited for bending, stamping and other cold forming processes. The alloy may be soldered, brazed or welded.

As the zinc content increases, the strength improves, yet the conductivity and ductility are reduced. CuZn15 has a good resistance to stress corrosion cracking, yet the alloy should be stress relieved if exposed to an ammonia atmosphere.

Due to the raised zinc content brass has economical advantages.

CuZn15 is a widely used alloy with an excellent combination of strength, ductility and corrosion resistance.

Fields of application are stamped and deep drawn products, dry goods, jewelry, cosmetic packaging and components of mechanical and electrical engineering and building technology.

## Composition

Cu	Fe	Pb	Zn	Al	Ni	Sn
[%]	[%]	[%]	[%]	[%]	[%]	[%]
84-86	0.05 max	0.05 max	rem	0.02 max	0.3 max	0.1 max

Composition of this alloy is in accordance with RoHS for electric & electronic components and ELV for the automotive industry.

## Physical properties

Melting point	Density	c <sub>p</sub> @ 20°C	Young's modulus	Thermal cond.	Electrical cond.		α @20-300°C
					[MS/m]	[%IACS]	
[°C]	[g/cm <sup>3</sup> ]	[kJ/kgK]	[GPa]	[W/mK]			[10 <sup>-6</sup> /K]
1027	8.75	0.38	122	159	≥ 21	≥36	18.7

Note: The specified conductivity applies to the soft condition only.

c<sub>p</sub> specific heat capacity  
 α coefficient of thermal expansion

## Mechanical properties

	Tensile Strength	Yield Strength	Elongation A <sub>50</sub>	Hardness HV	Bend ratio 90° [r]		Bend ratio 180° [r]	
					GW	BW	GW	BW
	[MPa]	[MPa]	[%]	[-]				
R260	260-310	≤ 170	≥ 36	55-85	0	0	0	0
R300	300-370	≥ 150	≥ 16	85-115	0	0	0	0
R350	350-420	≥ 250	≥ 4	105-135	0	0	0	0
R410	410-490	≥ 360	≥ 2	125-155	0	1	0.5	1
R480	480-560	≥ 430	≥ 1	≥ 150	0.5	3	1	3.5
R550	≥ 550	≥ 500	-	-	0.5	1.5	1	3

r = x \* t (thickness t ≤ 0.5mm)

GW bend axis transverse to rolling direction. BW bend axis parallel to rolling direction.

**Fabrication properties**

<b>Cold formability</b>	excellent
<b>Hot formability</b>	good
<b>Soldering</b>	excellent
<b>Brazing</b>	excellent
<b>Oxyacetylene welding</b>	good
<b>Gas shielded arc welding</b>	good
<b>Resistance welding</b>	fair
<b>Machinability</b>	fair

**Electrical conductivity**

The electrical conductivity depends on chemical composition, the level of cold deformation and the grain size. A high level of deformation as well as a small grain size decrease the conductivity.

**Corrosion Resistance**

Brass is resistant to: Natural, industrial and salt bearing atmospheres, drinking water, alkaline and neutral saline solutions.  
 Brass is not resistant to: Acids, ammonia, halogenide, cyanide and hydrogen sulfide solutions and atmospheres as well as sea water (especially at high flow rates).  
 CuZn15 has a low sensitivity to stress corrosion cracking and is resistant to dezincification, different to brass alloys with higher zinc contents. Yet the alloy should be stress relieved if stress corrosion cracking might be an issue.

**Typical uses**

Architectural, stamped and deep drawn products, jewelry, dry goods, cosmetic packaging, components of electrical engineering, mechanical and building engineering.

This leaflet is for general information only and is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The data given are no warranty that the product is of a specified quality and they cannot replace expert advice or the customer's own test.