

CuZn37

18 05

Comparable standards: UNS C27200 • EN CW508L • JIS C2720

Aurubis designations: C272/C274 • PNA 243 • SM1063

Description

CuZn37 is a solid solution strengthened copper alloy (brass) with 37% zinc.

The alloy has good cold forming properties and is economically interesting due to the high zinc content. CuZn37 can be brazed and soldered, welding processes need to be executed with care, due to the high zinc content.

As the zinc content increases in the alloy, the strength improves yet the conductivity and ductility are reduced. Moreover, it should be noted that as the zinc content rises, the tendency to stress corrosion cracking increases in the event of exposure to an ammonia atmosphere. This type of corrosion can, however, be countered in many cases by the removal of internal stress.

Fields of application are deep drawn parts, metal ware, components of electrical engineering, connectors, mechanical engineering, signs and decoration as well as musical instruments.

Composition

Cu	Fe	Pb	Zn	Al	Ni	Sn
[%]	[%]	[%]	[%]	[%]	[%]	[%]
62-64.0	0.1 max	0.1 max	rem	0.05 max	0.3 max	0.1 max

This alloy is in accordance with RoHS 2002/96/CE for electric & electronic components and 2002/53/CE for the automotive industry.

Physical properties

Melting point	Density	c _p @ 20°C	Young's modulus	Thermal cond.	Electrical cond.		α @ 20°C
					[MS/m]	[%IACS]	
[°C]	[g/cm ³]	[kJ/kgK]	[GPa]	[W/mK]			[10 ⁻⁶ /K]
920	8.4	0.377	110	116	≥ 16	≥ 28	20.5

Note: The specified conductivity applies to the soft condition only.

c_p specific heat capacity

α coefficient of thermal expansion

Mechanical properties

	Tensile Strength	Yield Strength	Elongation A ₅₀	Hardness HV	Bend ratio 90° [r]		Bend ratio 180° [r]	
					GW	BW	GW	BW
	[MPa]	[MPa]	[%]	[-]				
R300	300-370	≤ 180	≥ 38	55-95	0	0	0	0
R350	350-440	≥ 170	≥ 19	95-125	0	0	0	0
R410	410-490	≥ 300	≥ 8	120-155	0	0	0	1
R480	480-560	≥ 430	≥ 3	150-180	0	0.5	1	2
R550	≥ 550	≥ 500	-	≥ 170	1	2	3	4

Other tempers are available upon request.

r = x * t (thickness t ≤ 0.5mm)

GW bend axis transverse to rolling direction. BW bend axis parallel to rolling direction.

Fabrication properties

Cold formability	excellent
Hot formability	not recommended
Soldering	excellent
Brazing	excellent
Oxyacetylene welding	fair
Gas shielded arc welding	fair
Resistance welding	good
Machinability	fair

Electrical conductivity	The electrical conductivity depends on chemical composition, the level of cold deformation and the grain size. A high level of deformation as well as a small grain size decrease the conductivity.
Corrosion Resistance	<p>Brass is resistant to: Natural, industrial and salt bearing atmospheres, drinking water, alkaline and neutral saline solutions.</p> <p>Brass is not resistant to: Acids, ammonia, halogenide, cyanide and hydrogen sulfide solutions and atmospheres as well as sea water (especially at high flow rates).</p> <p>Under certain circumstances (high Cl content and low carbon-hardness) dezincification can be an issue with β - phase bearing alloys. The alloy also has a certain sensitivity to stress corrosion cracking when exposed to certain environments (e.g. ammonia, amine or sal ammoniac). The alloy should be stress relieved if stress corrosion cracking might be an issue.</p>
Typical uses	Metal ware, electric and mechanical engineering, connectors, electric brackets, clips & contacts, radiator cores & tanks, holloware base metal, lamps, bowls, trays, flashlight socket shells, grommets, eyelets, fasteners, bead chain, hardware items as knobs, roses, hinges, stencils, springs, cartridge & shell cases, hose couplings, decorative pots and planters, musical instruments

This leaflet is for general information only and is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The data given are no warranty that the product is of a specified quality and they cannot replace expert advice or the customer's own test.